



Rhinossorb® 622

Hindered amine light stabilizer (HALS)

Chemical Name: Poly(4-hydroxy-2,2,6,6-tetramethyl-1-piperidine ethanol-alt-1,4-butanedioicacid)

CAS NO.: 65447-77-0

Structure:

Features

Rhinossorb 622 is a polymeric high molecular weight hindered amine light stabilizer, with low volatility, migration resistance, low alkalinity and high temperature resistance. It has synergetic effect with antioxidants and UV absorbers.

Applications

It is effective in a broad range of polymers and applications. The product is particularly usefully in PE applications (injection molding, rotational molding, film, and tape), EVA, PP fibers, polyurethanes, polyacetals, polyamide, elastomers, adhesives etc. It is usually used in combination with antioxidants, UV absorbers to optimize performance in outdoor use.

Typical properties

Appearance	White or white like solid
Light transmittance	≥98% (425nm) ≥99% (500nm)
Molecular weight	≥3000 g/mol
Melting point	50-70°C
Loss on drying	≤0.5%
Ash	≤0.1%





Package & Storage

Package: 25kg carton inner with plastic bag or as customer`s requirement. Storage: Keep container tightly closed in a dry and well-ventilated place.

Safety

The use of proper protective equipment is recommended. Excess exposure to the product—should be avoided. Wash thoroughly after handling.

All safety information is provided in the Safety Data Sheet.

Note

The descriptions, designs, data and information contained herein are presented in good faith and are based on RHINOCHEM's current knowledge and experience. They are provided for guidance only, and do not constitute the agreed contractual quality of the product or a part of RHINOCHEM's terms and conditions of sale.

Because many factors may affect processing or application/use of the product, RHINOCHEM recommends that the reader carry out its own investigations and tests to determine the suitability of a product for its particular purpose prior to use. It is the responsibility of the recipient of product to ensure that any proprietary rights and existing laws and legislation are observed. No warranties of any kind, either expressed or implied, including, but not limitedto, warranties of merchantability or fitness for a particular purpose, are maderegarding products described or designs, data or information set forth herein,or that the products, descriptions, designs, data or information may be used without infringing the intellectual property rights of others. Any descriptions, designs, data and information given in this publication may change without prior information. The descriptions, designs, data and information furnished by RHINOCHEM hereunder are given gratis and RHINOCHEM assumes no obligation or liability for the descriptions, designs, data or information given or results obtained, all such being given and accepted at the reader's risk.

