


Rhinuva[®] 326

Ultraviolet Absorber 326 (UV-A)

Chemical Name: 2-(5-Chloro-2H-benzotriazole-2-yl)-6-(1,1-di-methylethyl)-4-methylphenol

CAS NO.: 3896-11-5

Structure:



Features

UV Absorber 326 is a strong absorber of ultraviolet radiation in the 300-400nm region. It has a low volatility at high temperatures and resistance to thermal degradation and can therefore be used without significant loss or decomposition in the polyolefin compounding and molding processes.

Applications

The product is mainly used for polyvinyl chloride, polystyrene, unsaturated resin, polycarbonate, polymethyl methacrylate, polyethylene, ABS resin, epoxy resin etc. It can be used in combination with phenolic & phosphite antioxidants, and HALS to optimize performance in outdoor use.

Typical properties

Appearance	Light yellow powder	
Purity	≥99%	
Light transmittance	≥93% (460nm)	≥95% (500nm)
Melting point	137-142°C	
Loss on drying	≤0.5%	
Ash	≤0.1%	

Package & Storage

Package: 25kg carton inner with plastic bag or as customer`s requirement.
Storage: Keep container tightly closed in a dry and well-ventilated place.

Safety

The use of proper protective equipment is recommended. Excess exposure to the product should be avoided. Wash thoroughly after handling.
All safety information is provided in the Safety Data Sheet.

Note

The descriptions, designs, data and information contained herein are presented in good faith and are based on RHINO CHEM`s current knowledge and experience. They are provided for guidance only, and do not constitute the agreed contractual quality of the product or a part of RHINO CHEM`s terms and conditions of sale.

Because many factors may affect processing or application/use of the product, RHINO CHEM recommends that the reader carry out its own investigations and tests to determine the suitability of a product for its particular purpose prior to use. It is the responsibility of the recipient of product to ensure that any proprietary rights and existing laws and legislation are observed. No warranties of any kind, either expressed or implied, including, but not limited to, warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth herein, or that the products, descriptions, designs, data or information may be used without infringing the intellectual property rights of others. Any descriptions, designs, data and information given in this publication may change without prior information. The descriptions, designs, data and information furnished by RHINO CHEM hereunder are given gratis and RHINO CHEM assumes no obligation or liability for the descriptions, designs, data or information given or results obtained, all such being given and accepted at the reader`s risk.